

Winch Solutions Ltd

12-Strand Synthetic Rope Breaking Strength Test Report

The Operator:___

Test date:2016-02-24 10:20:00

Diameter:11mm

Material:UHMWPE


Customer:

Temperature: 20 °C

PIN: 58611001

Remark:

	Diameter	The maximum force (Fm)	Tensile strength(Rm)
Unit	mm	N	MPa
Sample 1	11	130595.906	1384.235
Sample 2	11	128825.914	1363.465
sample 3	11	134325.615	1405.520
Maximum	11.000	134325.615	1405.520
Minimum	11.000	128825.914	1363.465
Average	11.000	131249.150	1384.410



Approval:

Review:

The operator: Sihai Li

Date:2016-02-24